

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 0.25 PHR Thanecure ZM

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Thanecure ZM is an activator for a sulfur cure of Millathane® millable polyurethanes consisting of a partial complex of zinc chloride and MBTS. All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-025-PHR-Thanecure-ZM.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-025-PHR-Thanecure-ZM.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	
Tensile Strength, Yield	33.72 MPa	4891 psi	
Elongation at Yield	646 %	646 %	
100% Modulus	0.00301 GPa	0.437 ksi	
200% Modulus	0.00671 GPa	0.973 ksi	
300% Modulus	0.01184 GPa	1.717 ksi	
Tear Strength	58.5 kN/m	334 pli	Die C
Compression Set	40.6 % @Temperature 70.0 °C, Time 79200 sec	40.6 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	16.1 min @Temperature 155 °C	0.268 hour @Temperature 311 °F	TC90

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

