

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 10.0 PHR Benzoflex 9-88SG Plasticizer

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Plasticizers should be used in all Millathane®76 compounds to better incorporate fillers and improve processing. Some plasticizers are not compatible with Millathane76, e.g. naphthenic and all paraffinic oils, however, a number of ester plasticizers perform very well. Formulation Millathane 76 100.0 Zinc Stearate 0.5 N-550 Black 40.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 Plasticizer 10.0 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-100-PHR-Benzoflex-9-88SG-Plasticizer.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-100-PHR-Benzoflex-9-88SG-Plasticizer.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
	80	80	heat aged 70 hours @ 100°C
Tensile Strength, Yield	24.28 MPa	3522 psi	
Elongation at Yield	541 %	541 %	
100% Modulus	0.00334 GPa	0.484 ksi	
200% Modulus	0.007853 GPa	1.139 ksi	
300% Modulus	0.01297 GPa	1.881 ksi	
Tear Strength	65.7 kN/m	375 pli	Die C
	31.2 %	31.2 %	
Compression Set	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-35.0 °C	-31.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	
	@Temperature 155 °C	@Temperature 311 °F	

Descriptive Properties	Value	Comments
Weight Loss (%)	2.7	heat aged 70 hours @ 100°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China