

TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 20 PHR Carbon Black, N-550 (FEF)

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0Zinc Stearate0.5Poly AC 617A1.0TP-9510.0Thanecure® ZM1.0MBTS4.0MBT2.0Sulfur1.5N-55020All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-20-PHR-Carbon-Black-N-550-FEF.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	
Tensile Strength, Yield	28.76 MPa	4171 psi	
Elongation at Yield	564 %	564 %	
100% Modulus	0.00227 GPa	0.329 ksi	
200% Modulus	0.00498 GPa	0.723 ksi	
300% Modulus	0.008770 GPa	1.272 ksi	
Tear Strength	59.9 kN/m	342 pli	
Taber Abrasion, mg/1000 Cycles	7.0 @Load 1.00 kg	7.0 @Load 2.20 lb	H-18 wheel
Compression Set	51.7 % @Temperature 70.0 °C, Time 79200 sec	51.7 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min @Temperature 154 °C	0.167 hour @Temperature 309 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China