

TSE Industries Millathane® CM Millable Polyether Urethane Rubber with 120 PHR N220 Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents.FormulationMillathane CM 100.0N220120.0Coumarone-Indene Resin40.0MBTS4.0MBT1.0Sulfur0.75CAYTUR 40.35Zinc Stearate0.50All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-with-120-PHR-N220-Filler.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	
Mooney Viscosity	80	80	
wooney viscosity	@Temperature 121 °C	@Temperature 250 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	
Tensile Strength, Yield	23.4 MPa	3400 psi	
Elongation at Yield	250 %	250 %	
100% Modulus	0.0117 GPa	1.70 ksi	
Tear Strength	67.9 kN/m	387 pli	Graves
Abrasion	220	220	NBS Index
Compression Set	48 %	48 %	Method B

	Processing Properties	Metric	English	Comments
Cure Time	Cura Tima	60.0 min	1.00 hour	
	@Temperature 142 °C	@Temperature 287 °F		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com



Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China