

TSE Industries Millathane® CM Millable Polyether Urethane Rubber with 75 PHR N774 Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. Formulation Millathane CM 100.0N77475.0Coumarone-Indene Resin25.0MBTS4.0MBT1.0Sulfur0.75CAYTUR 40.35Zinc Stearate0.50All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-with-75-PHR-N774-Filler.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	
Mooney Viscosity	37	37	
	@Temperature 121 °C	@Temperature 250 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	
Tensile Strength, Yield	23.1 MPa	3350 psi	
Elongation at Yield	520 %	520 %	
100% Modulus	0.00431 GPa	0.625 ksi	
300% Modulus	0.0169 GPa	2.45 ksi	
Tear Strength	67.0 kN/m	382 pli	Graves
Abrasion	150	150	NBS Index
Compression Set	19 %	19 %	Method B

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 142 °C	@Temperature 287 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China