

## TSE Industries Millathane® CM Millable Polyether Urethane Rubber with 90 PHR N650 Filler

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. Formulation Millathane CM 100.0N65090.0Coumarone-Indene Resin30.0MBTS4.0MBT1.0Sulfur0.75CAYTUR 40.35Zinc Stearate0.50All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-with-90-PHR-N650-Filler.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-with-90-PHR-N650-Filler.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	
Mooney Viscosity	39	39	
	@Temperature 121 °C	@Temperature 250 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	
Tensile Strength, Yield	23.4 MPa	3400 psi	
Elongation at Yield	450 %	450 %	
100% Modulus	0.00689 GPa	1.00 ksi	
300% Modulus	0.0197 GPa	2.85 ksi	
Tear Strength	72.2 kN/m	412 pli	Graves
Abrasion	215	215	NBS Index
Compression Set	23 %	23 %	Method B

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 142 °C	@Temperature 287 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China