

TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane, 330°F Cure Temperature

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Formulation Millathane HT 100.0 Zinc Stearate 0.5 MBTS 4.0 MBT 2.0 N-330 Black 20.0 Sulfur 1.5 THANECURE® ZM1.0 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-330F-Cure-Temperature.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	
Tensile Strength, Yield	26.90 MPa	3901 psi	
Elongation at Yield	437 %	437 %	
100% Modulus	0.00281 GPa	0.408 ksi	
200% Modulus	0.007426 GPa	1.077 ksi	
300% Modulus	0.01404 GPa	2.036 ksi	
Tear Strength	44.6 kN/m	254 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	13.0 min	0.217 hour	
	@Temperature 166 °C	@Temperature 330 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China