

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane, Hardness 61A

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Carbon Black with Sulfur Cure System Formulation Millathane HT100.0N-330 Black20.0MBTS4.0MBT2.0Zinc Stearate0.5THANECURE® ZM1.0Sulfur1.5All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-Hardness-61A.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-Hardness-61A.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	61	61	
Tensile Strength, Yield	27.15 MPa	3938 psi	
Elongation at Yield	464 %	464 %	
100% Modulus	0.00285 GPa	0.413 ksi	
200% Modulus	0.007212 GPa	1.046 ksi	
300% Modulus	0.01320 GPa	1.914 ksi	
Tear Strength	45.3 kN/m	258 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	20.0 min	0.333 hour	
	@Temperature 149 °C	@Temperature 300 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China