

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 1.0 PHR Zinc Stearate

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Zinc stearate, when used as a co-activator with THANECURE® ZM, permits shorter cure times with improved compression set properties. Zinc stearate does contribute some lubricity to the batch and helps prevent sticking to mill rolls and surfaces of internal mixers, however its primary use is to help activate the cure and produce a tighter cure. All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-10-PHR-Zinc-Stearate.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-10-PHR-Zinc-Stearate.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84	84	
Tensile Strength, Yield	17.46 MPa	2533 psi	
Elongation at Yield	369 %	369 %	
100% Modulus	0.00572 GPa	0.830 ksi	
200% Modulus	0.01170 GPa	1.697 ksi	
300% Modulus	0.01598 GPa	2.317 ksi	
Tear Strength	39.0 kN/m	223 pli	Die C
Compression Set	61 % @Temperature 70.0 °C, Time 79200 sec	61 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	12.0 min @Temperature 160 °C	0.200 hour @Temperature 320 °F	Press cured

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	123	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China