

TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 3.0 PHR MBT

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. An increase in the level of MBTS results in more processing safety, plus it gives a higher state of cure. On the other hand, MBT acts as an accelerator which, when increased, will cause a decrease in processing safety and a higher state of cure. All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-30-PHR-MBT.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	79	79	
Tensile Strength, Yield	18.64 MPa	2704 psi	
Elongation at Yield	408 %	408 %	
100% Modulus	0.00551 GPa	0.799 ksi	
200% Modulus	0.01157 GPa	1.678 ksi	
300% Modulus	0.0161 GPa	2.34 ksi	
Tear Strength	39.0 kN/m	223 pli	Die C
Compression Set	61 % @Temperature 70.0 °C, Time 79200 sec	61 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	11.0 min @Temperature 160 °C	0.183 hour @Temperature 320 °F	Press cured

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	131	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China