

Taiwan PU Corporation CPU-69-A/B Mixing Ratio 100/26 Polyurethane Casting Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Compound of CPU-69-A/B with a mixing ratio of 100/26. Information provided by Taiwan PU Corporation. MatWeb has a separate entry for the unmixed A and B components.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-CPU-69-AB-Mixing-Ratio-10026-Polyurethane-Casting-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	
Tensile Strength at Break	1.86 MPa	270 psi	
Elongation at Break	350 %	350 %	
Tear Strength	19.6 kN/m	112 pli	

Descriptive Properties	Value	Comments
Mixing Ratio	100/26	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China