

Techmer ES Elastoblend® PA6/6 IM L W Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

Availability: North America Forms: Pellets Additive: Lubricant and Impact Modifier Features: Lubricant and Impact Modified Processing

Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA66-IM-L-W-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ASTM D792
Water Absorption	1.3 % @Time 86400 sec	1.3 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.016 cm/cm @Thickness 3.17 mm	0.016 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength	52.4 MPa	7600 psi	ASTM D638
Elongation at Yield	48 %	48 %	ASTM D638
Flexural Yield Strength	79.3 MPa	11500 psi	ASTM D790
Flexural Modulus	1.72 GPa	250 ksi	ASTM D790
Izod Impact, Notched	1.82 J/cm @Thickness 3.17 mm, Temperature -40.0 °C	3.40 ft-lb/in @Thickness 0.125 in, Temperature -40.0 °F	ASTM D256
	8.54 J/cm @Thickness 3.17 mm, Temperature 22.8 °C	16.0 ft-lb/in @Thickness 0.125 in, Temperature 73.0 °F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	79.2 µm/m-°C	44.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	216 °C	420 °F	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (104 psi)	77.3 °C	169.1 °F	ASTM D648
Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+14 ohm-cm	2.00e+14 ohm-cm	ASTM D257
Dielectric Strength	17.3 kV/mm	440 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China