

## Techmer ES Electrablend® ABS SS15 BK MB 15% Stainless Steel Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Stainless Steel Fiber Filled

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Stainless Steel Fiber, 15% Filler by Weight  
Features: Electromagnetic Shielding (EMI)  
Appearance: Black  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Electrablend-ABS-SS15-BK-MB-15-Stainless-Steel-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-SS15-BK-MB-15-Stainless-Steel-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.28 % @Time 86400 sec	0.28 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.3 MPa	7300 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	3.38 GPa	490 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	2.40 J/cm @Thickness 3.17 mm	4.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.6 Åµm/m-Å°C	47.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	102 Å°C	215 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	96.1 Å°C	205 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.0 - 10 ohm-cm Metric	1.0 - 10 ohm-cm English	ASTM D257 Comments
Surface Resistance	1.0 - 10 ohm	1.0 - 10 ohm	ASTM D257
Shielding Effectiveness	55 dB @Frequency 3.00e+7 - 1.00e+9 Hz	55 dB @Frequency 3.00e+7 - 1.00e+9 Hz	ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China