

Techmer ES Electrablend® ABS SS7 BK MB 7% Stainless Steel Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Stainless Steel Fiber Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Stainless Steel Fiber, 7% Filler by Weight Features: ESD

Protection Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-SS7-BK-MB-7-Stainless-Steel-Filled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792
Water Absorption	0.28 % @Time 86400 sec	0.28 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.3 MPa	7300 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	3.10 GPa	450 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	2.40 J/cm @Thickness 3.17 mm	4.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.6 Åµm/m-Å°C	47.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	102 Å°C	215 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	96.1 Å°C	205 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	10000 - 1.00e+6 ohm- Metric	10000 - 1.00e+6 ohm- English	Comments
Surface Resistance	10000 - 1.00e+6 ohm	10000 - 1.00e+6 ohm	ASTM D257
Shielding Effectiveness	40 dB @Frequency 3.00e+7 - 1.00e+9 Hz	40 dB @Frequency 3.00e+7 - 1.00e+9 Hz	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China