

## Techmer ES Electrablend® PA6/6 03001 Carbon Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Carbon Fiber Filled , Nylon 66, Conductive , Nylon 66, Heat Stabilized , Nylon 66, Impact Grade

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Carbon Fiber Reinforcement Additive: Impact Modifier and Heat Stabilizer Features: Electrically Conductive, Impact Modified and Heat Stabilized Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Electrablend-PA66-03001-Carbon-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-PA66-03001-Carbon-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.90 %	0.90 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.010 cm/cm	0.010 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	111	111	ASTM D785
Tensile Strength, Yield	121 MPa	17500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	165 MPa	24000 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.92 J/cm	3.60 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Izod Impact, Unnotched	10.1 J/cm	19.0 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	39.6 Åµm/m-Å°C	22.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	252 Å°C	485 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	220 Å°C	428 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	10000 - 1.00e+6 ohm-cm	10000 - 1.00e+6 ohm-cm	ASTM D257
Surface Resistance	10000 - 1.00e+6 ohm	10000 - 1.00e+6 ohm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China