

Techmer ES Electrablend® PA6/6 CF20 L BK 20% Carbon Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Carbon Fiber Filled , Nylon 66, Conductive

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Carbon Fiber Reinforcement, 20% Filler by Weight Additive:

Lubricant Features: Electrically Conductive and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-PA66-CF20-L-BK-20-Carbon-Filled.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ASTM D792
Water Absorption	0.85 % @Time 86400 sec	0.85 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	179 MPa	26000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	276 MPa	40000 psi	ASTM D790
Flexural Modulus	16.2 GPa	2350 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 3.17 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 Åµm/m-Å°C	38.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	259 Å°C	498 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 - 1.00e+6 ohm-cm	100 - 1.00e+6 ohm-cm	ASTM D257
Surface Resistance	100 - 1.00e+6 ohm	100 - 1.00e+6 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China