

Techmer ES Electrablend® PA6/6 CF30 BK 30% Carbon Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Carbon Fiber Filled , Nylon 66, Conductive

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Carbon Fiber Reinforcement, 30% Filler by Weight Additive:

Lubricant Features: Electrically Conductive and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-PA66-CF30-BK-30-Carbon-Filled.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ASTM D792
Water Absorption	0.48 % @Time 86400 sec	0.48 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Thickness 3.17 mm	0.0020 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	97	97	ASTM D785
Tensile Strength, Yield	234 MPa	34000 psi	ASTM D638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D638
Flexural Strength	345 MPa	50000 psi	ASTM D790
Flexural Modulus	0.0000193 GPa	0.00280 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	6.41 J/cm @Thickness 3.17 mm	12.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	18.0 Åµm/m-Å°C	10.0 Åµin/in-Å°F	ASTM D696
Melting Point	263 Å°C	505 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	260 Å°C	500 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	257 Å°C	495 Å°F	Unannealed; ASTM D648

Flammability UL 94 Thermal Properties	HB Metric	HB English	Comments
Electrical Properties	Metric	English	Comments
Surface Resistance	100 - 200 ohm	100 - 200 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China