

Techmer ES Electrafil[®] J-50/CF/10/TF/15 Polycarbonate, 10% Carbon Fiber Reinforced, 15% PTFE

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon + PTFE Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrafil-J-50CF10TF15-Polycarbonate-10-Carbon-Fiber-Reinforced-15-PTFE.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ASTM D792
Water Absorption	0.15 %	0.15 %	24 hrs. ASTM D570
Linear Mold Shrinkage	0.0020 cm/cm @Thickness 3.17 mm	0.0020 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	96.5 MPa	14000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Yield Strength	131 MPa	19000 psi	ASTM D790
Flexural Modulus	6.76 GPa	980 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	148 Â°C	298 Â°F	ASTM D648

Electrical Properties	Metric	English	Comments
Electrical Resistivity	100 - 1000 ohm-cm	100 - 1000 ohm-cm	ASTM C611
Surface Resistance	10000 ohm - 1e+05	10000 ohm - 1e+05	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China