

Techmer ES HiFill® ABS GF30 BK 30% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Glass Fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight
Appearance: Black
TPCI# 1018121
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-ABS-GF30-BK-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ASTM D792
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 cm/cm @Thickness 3.17 mm	0.0010 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	ASTM D785
Tensile Strength, Yield	100 MPa	14500 psi	ASTM D638
Elongation at Break	3.3 %	3.3 %	ASTM D638
Flexural Strength	128 MPa	18500 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	4.00 J/cm @Thickness 3.17 mm	7.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	28.8 Åµm/m-Å°C	16.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	112 Å°C	233 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	103 Å°C	218 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+16 ohm-cm Metric	1.00e+16 ohm-cm English	ASTM D257 Comments
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China