

Techmer ES HiFill® ABS IM TM20 20% Mineral Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Mineral Filler, 20% Filler by Weight Additive: Impact Modifier Features: Impact Modified Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-ABS-IM-TM20-20-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.13 %	0.13 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0015 cm/cm	0.0015 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	107	107	ASTM D785
Tensile Strength	73.1 MPa	10600 psi	ASTM D638
Elongation at Yield	3.5 %	3.5 %	ASTM D638
Flexural Yield Strength	109 MPa	15800 psi	ASTM D790
Flexural Modulus	3.93 GPa	570 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Izod Impact, Unnotched	5.07 J/cm	9.50 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	34.2 Åµm/m-Å°C	19.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	112 Å°C	233 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	103 Å°C	218 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China