

Techmer ES HiFill FR[®] PA6/6 GF50 FR BK 50% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 50% Glass Fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber, 50% Filler by Weight
Features: Flame Retardant
Appearance: Black
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA66-GF50-FR-BK-50-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.69 g/cc	0.0611 lb/in ³	ASTM D792
Water Absorption	0.35 % @Time 86400 sec	0.35 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Thickness 3.17 mm	0.0020 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	200 MPa	29000 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	296 MPa	43000 psi	ASTM D790
Flexural Modulus	16.5 GPa	2400 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm @Thickness 3.17 mm	1.90 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	9.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	260 $\text{Å}^\circ\text{C}$	500 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	1.97 kV/mm	50.0 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China