

Techmer ES HiFill FR[®] PET GF30 FR X 30% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber, 30% Filler by Weight Features: Flame Retardant Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PET-GF30-FR-X-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.67 g/cc	0.0603 lb/in ³	ASTM D792
Water Absorption	0.050 % @Time 86400 sec	0.050 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 cm/cm @Thickness 3.17 mm	0.0090 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	134 MPa	19500 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Yield Strength	193 MPa	28000 psi	ASTM D790
Flexural Modulus	10.3 GPa	1500 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm @Thickness 3.17 mm	1.70 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	91.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	51.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	246 $\text{Å}^\circ\text{C}$	475 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	224 $\text{Å}^\circ\text{C}$	435 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China