

Techmer ES HiFill[®] HDPE GF25 CC 25% Glass Filled

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Glass fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 25% Filler by Weight
Features: Chemically Coupled
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-HDPE-GF25-CC-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Water Absorption	0.030 % @Time 86400 sec	0.030 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	76	76	ASTM D785
Tensile Strength, Yield	48.3 MPa	7000 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm @Thickness 3.17 mm	3.00 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	6.94 J/cm @Thickness 3.17 mm	13.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	54.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	30.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	129 $\text{Å}^\circ\text{C}$	265 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	121 $\text{Å}^\circ\text{C}$	250 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China