

## Techmer ES HiFill<sup>®</sup> PA6 CF30 30% Carbon Fiber Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Carbon Fiber Filled

**Material Notes:**

Availability: North America  
 Forms: Pellets  
 Filler/Reinforcement: Carbon Fiber Reinforcement, 30% Filler by Weight  
 Appearance: Black and Natural Color  
 Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA6-CF30-30-Carbon-Fiber-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-CF30-30-Carbon-Fiber-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.0 % @Time 86400 sec	1.0 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	214 MPa	31000 psi	ASTM D638
Elongation at Break	1.5 %	1.5 %	ASTM D638
Flexural Strength	310 MPa	45000 psi	ASTM D790
Flexural Modulus	17.2 GPa	2500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	23.4 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	13.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	216 $\text{Å}^\circ\text{C}$	420 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 $\text{Å}^\circ\text{C}$	410 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**