

## Techmer ES HiFill<sup>®</sup> PA6 GF20 RM BK 20% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 20% Filler by Weight Features: Low Moisture Absorption Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA6-GF20-RM-BK-20-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF20-RM-BK-20-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.90 % @Time 86400 sec	0.90 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	138 MPa	20000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	11.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	204 $\text{Å}^\circ\text{C}$	400 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China