

## Techmer ES HiFill<sup>®</sup> PA6 GF30 L UV BK 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight  
Processing Method: Injection Molding  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA6-GF30-L-UV-BK-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF30-L-UV-BK-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.3 % @Time 86400 sec	1.3 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	165 MPa	24000 psi	ASTM D638
Elongation at Break	2.4 %	2.4 %	ASTM D638
Flexural Strength	234 MPa	34000 psi	ASTM D790
Flexural Modulus	1.03 GPa	150 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	9.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	216 $\text{Å}^\circ\text{C}$	420 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 $\text{Å}^\circ\text{C}$	410 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	16.1 kV/mm	410 kV/in	Method A (Short-Time); ASTM D149

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**