

Techmer ES HiFill[®] PA6 GF50 LE 50% Glass Filled (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 50% Filler by Weight Additive: Lubricant Features:

Low Extractables and Lubricated Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF50-LE-50-Glass-Filled-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.57 g/cc	0.0567 lb/in ³	ASTM D792
Water Absorption	0.75 % @Time 86400 sec	0.75 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0025 cm/cm @Thickness 3.17 mm	0.0025 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	193 MPa	28000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	269 MPa	39000 psi	ASTM D790
Flexural Modulus	10.7 GPa	1550 ksi	ASTM D790
Izod Impact, Notched	2.67 J/cm @Thickness 3.17 mm	5.00 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China