

Techmer ES HiFill® PA6/6 E4 IM Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Availability: North America Forms: Pellets Features: Good Toughness and High Viscosity Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-E4-IM-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	1.2 %	1.2 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength, Yield	80.0 MPa	11600 psi	ASTM D638
Elongation at Break	80 %	80 %	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	2.69 GPa	390 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	77.4 Åµm/m-Å°C	43.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	237 Å°C	459 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.2 Å°C	180 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China