

Techmer ES HiFill[®] PA6/6 GF25 HS L 25% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 25% Filler by Weight
Additive: Heat Stabilizer and Lubricant
Features: Lubricated and Heat Stabilized
Processing Method: Injection Molding
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF25-HS-L-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ASTM D792
Water Absorption	1.8 % @Time 86400 sec	1.8 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	165 MPa	24000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	214 MPa	31000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.854 J/cm @Thickness 3.17 mm	1.60 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	11.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	255 $\text{Å}^\circ\text{C}$	491 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	250 $\text{Å}^\circ\text{C}$	482 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	19.3 kV/mm	490 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China