

## Techmer ES HiFill® PA6/6 GF33 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 33% Filler by Weight Additive: Lubricant Features: Lubricated TPCI# 8682101 Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA66-GF33-33-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF33-33-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.55 % @Time 86400 sec	0.55 % @Time 24.0 hour	ASTM D570
Water Absorption at Saturation	5.1 %	5.1 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	190 MPa	27500 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	221 MPa	32000 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Shear Strength	83.4 MPa	12100 psi	ASTM D732
Izod Impact, Notched	1.17 J/cm @Thickness 3.17 mm	2.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	32.4 Åµm/m-Å°C	18.0 Åµin/in-Å°F	ASTM D696
Melting Point	259 Å°C	499 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	263 Å°C	505 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	259 Å°C	499 Å°F	Unannealed; ASTM D648

Flammability UL 94 Thermal Properties	HB Metric	HB English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	ASTM D257
Dielectric Strength	19.7 kV/mm	500 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China