

Techmer ES HiFill® POM CO 0167 S2 LE Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Steel Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Metal Features: Copolymer and Low Extractables Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-POM-CO-0167-S2-LE-Acetal.php

Physical Properties	Metric	English	Comments
Density	1.67 g/cc	0.0603 lb/in ³	ASTM D792
Water Absorption	0.20 % @Time 86400 sec	0.20 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.016 cm/cm @Thickness 3.17 mm	0.016 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 190 °C	9.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	3.03 GPa	440 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 µm/m-°C	12.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China