

Techmer ES HiFill® PP CO GF43 CC 43% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 40% Glass Fiber Filler

Material Notes:

Availability: North America
 Forms: Pellets
 Filler/Reinforcement: Glass Fiber Reinforcement, 43% Filler by Weight
 Features: Copolymer and Chemically Coupled
 Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-CO-GF43-CC-43-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.050 % @Time 86400 sec	0.050 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.035 cm/cm @Thickness 3.17 mm	0.035 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	75.8 MPa	11000 psi	ASTM D638
Elongation at Break	5.5 %	5.5 %	ASTM D638
Flexural Strength	128 MPa	18500 psi	ASTM D790
Flexural Modulus	7.24 GPa	1050 ksi	ASTM D790
Izod Impact, Notched	2.08 J/cm @Thickness 3.17 mm	3.90 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	37.8 Åm/m-Å°C	21.0 Åin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	157 Å°C	315 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 Å°C	270 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China