

## Techmer ES Luriblend® HDPE GL5

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

**Material Notes:**

Availability: North America Forms: Pellets Additive: Graphite Powder Lubricant Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Luriblend-HDPE-GL5.php](http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-HDPE-GL5.php)

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.010 % @Time 86400 sec	0.010 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.030 cm/cm @Thickness 3.17 mm	0.030 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 190 °C	20 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	45	45	ASTM D785
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Flexural Strength	41.4 MPa	6000 psi	ASTM D790
Flexural Modulus	1.21 GPa	175 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	144 µm/m-°C	80.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	Unannealed; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**