

Techmer ES Luriblend® PA6/6 GF40 ML2 HS 40% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber, 40% Filler by Weight
Additive: Heat Stabilizer and Molybdenum Disulfide Lubricant(2%)
Features: Lubricated and Heat Stabilized
Appearance: Natural Color
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA66-GF40-ML2-HS-40-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ASTM D792
Water Absorption	0.60 % @Time 86400 sec	0.60 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0035 cm/cm @Thickness 3.17 mm	0.0035 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Yield	172 MPa	25000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	269 MPa	39000 psi	ASTM D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	7.47 J/cm @Thickness 3.17 mm	14.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.2 Åµm/m-Å°C	14.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	263 Å°C	505 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	260 Å°C	500 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	19.7 kV/mm	500 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China