

Teijin Panlite® LV-2225L Standard (mold release/ice color grade) Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Flame retardant and mold release grade with high fluidity, while maintaining intrinsic transparency of polycarbonate resin. It is suitable for thin wall injection moldings. Applications: Electric, electronic and business machine components that need flame retardance and transparency. Slightly thin wall or large moldings. Information provided by Teijin Chemicals Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teijin-Panlite-LV-2225L-Standard-mold-releaseice-color-grade-Polycarbonate-Resin.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Water Absorption	0.20 %	0.20 %	in water, 23°C, 24h; ISO 62
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm @Thickness 4.00 mm	0.0050 - 0.0070 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 4.00 mm	0.0050 - 0.0070 in/in @Thickness 0.157 in	
Melt Flow	21.6 g/10 min @Load 1.20 kg, Temperature 300 °C	21.6 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	61.0 MPa	8850 psi	50mm/min; ISO 527
Elongation at Break	>= 50 %	>= 50 %	50mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50mm/min; ISO 527
Tensile Modulus	2.40 GPa	348 ksi	1mm/min; ISO 527
Flexural Strength	93.0 MPa	13500 psi	2mm/min; ISO 178
Flexural Modulus	2.35 GPa	341 ksi	2mm/min; ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179
Charpy Impact, Notched	6.70 J/cm ²	31.9 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
	70.0 µm/m-°C	38.9 µin/in-°F	

CTE linear Thermal Properties	Metric @Temperature 20.0 Â°C	English @Temperature 68.0 Â°F	ISO 11359 Comments
CTE, linear, Transverse to Flow	70.0 Âµm/m-Â°C @Temperature 20.0 Â°C	38.9 Âµin/in-Â°F @Temperature 68.0 Â°F	ISO 11359
Deflection Temperature at 0.46 MPa (66 psi)	139 Â°C	282 Â°F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	126 Â°C	259 Â°F	ISO 75
Vicat Softening Point	146 Â°C	295 Â°F	50Â°C/hr, 50N; ISO 306
UL RTI, Electrical	125 Â°C @Thickness 1.47 mm	257 Â°F @Thickness 0.0579 in	UL 746B
UL RTI, Mechanical with Impact	115 Â°C @Thickness 1.47 mm	239 Â°F @Thickness 0.0579 in	UL 746B
UL RTI, Mechanical without Impact	125 Â°C @Thickness 1.47 mm	257 Â°F @Thickness 0.0579 in	UL 746B
Flammability, UL94	V-2 @Thickness 0.380 mm	V-2 @Thickness 0.0150 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.585	1.585	ASTM D542
Transmission, Visible	88 % @Thickness 3.00 mm	88 % @Thickness 0.118 in	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.0 @Frequency 1e+6 Hz	3.0 @Frequency 1e+6 Hz	IEC 60250
	3.1 @Frequency 100 Hz	3.1 @Frequency 100 Hz	IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243
Dissipation Factor	0.0010	0.0010	IEC 60250

Electrical Properties	@Frequency 100 Hz Metric	@Frequency 100 Hz English	Comments
	0.0090	0.0090	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	250 V	250 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China