

Teknor Apex APEX[®] 6500-75 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade , PVC, Wire and Cable Grade

Material Notes:

Notes: 60[°]C General Purpose; RoHS Compliant Uses: Connectors; Grommets; Plugs; Strain Reliefs
Forms: Pellets Processing Method: Injection Molding Agency Ratings: UL QMFZ2 .E54709 Wire Types: Molded Components Additional Information: Temperature Rating: 60[°]C
Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-APEX-6500-75-Polyvinyl-Chloride-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	15 seconds; ASTM D2240
Tensile Strength at Break	15.4 MPa	2240 psi	ASTM D638
Elongation at Break	350 %	350 %	ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 [°] C	140 [°] F	Continuous Use; ASTM D794
Brittleness Temperature	-35.0 [°] C	-31.0 [°] F	ASTM D746
UL RTI, Electrical	50.0 [°] C @Thickness 1.50 mm	122 [°] F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical with Impact	50.0 [°] C @Thickness 1.50 mm	122 [°] F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical without Impact	50.0 [°] C @Thickness 1.50 mm	122 [°] F @Thickness 0.0591 in	UL 746
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
Oxygen Index	22 %	22 %	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	174 [°] C	345 [°] F	Processing Temperature

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China