

Teknor Apex Sarlink® 3145D Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO)

Material Notes:

A high hardness, multi-purpose thermoplastic elastomer featuring excellent compression set and high temperature performance. Sarlink® 3145D can be processed by injection blow molding, molding or extrusion for applications such as grips, seals, gaskets, profiles and other articles. Processing and Handling (See more in property table) Sarlink® 3145D is a polypropylene based elastomer, which can be processed on conventional thermoplastic equipment for injection molding, extrusion and blow molding. This product has a wide processing window in most applications. Melt temperatures from 360°F to 430°F can be used. Do not exceed 450°F. Drying is recommended for extrusion and blow molding and any time the material is used from an unsealed package. Extrusion screen pack is 20 to 60 mesh. PURGING This product has excellent melt stability. Empty the barrel for idle periods of thirty (30) minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene. RECYCLING/REGRIND This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing. COLORING The use of polyolefin based color concentrates is recommended. Apply back pressure in injection molding to disperse color. BONDING/ASSEMBLY Thermal bonding techniques can be used to form high strength bonds. Adhesive bonding can be achieved with specialized adhesives. Bond strength is limited due to the polypropylene base of this material. STORAGE and HANDLING This product is available in 55 lb. foil lined bags (up to 2,200 lbs. per pallet) or 1,100 lb. polyethylene lined gaylords. It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling. Sarlink® was sold from DSM to Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sarlink-3145D-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D792
Viscosity	348000 cP @Shear Rate 206 1/s, Temperature 200 °C	348000 cP @Shear Rate 206 1/s, Temperature 392 °F	ASTM D3835

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	48	48	extruded sample; 5 sec. delay; ASTM D2240
	52	52	injection molded sample; 5 sec. delay; ASTM D2240
Tensile Strength at Break	16.50 MPa	2393 psi	Die C; Flow direction; ASTM D412
	18.00 MPa	2611 psi	Die C; Cross direction; ASTM D412
Elongation at Break	475 %	475 %	Die C; Flow direction; ASTM D412
	602 %	602 %	Die C; Cross direction; ASTM D412
100% Modulus	0.0128 GPa	1.86 ksi	Die C; Cross direction; ASTM D412

Mechanical Properties	0.0136 GPa Metric	1.97 ksi English	Die C; Flow direction; ASTM D412 Comments
Tear Strength	103 kN/m	588 pli	Die C; Cross direction; ASTM D624
Compression Set	43 %	43 %	22h/23Â°C; ASTM D395B
	76 %	76 %	22hr; ASTM D395B
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 204 Â°C	360 - 400 Â°F	Extrusion
	177 - 216 Â°C	350 - 420 Â°F	Injection Molding
Middle Barrel Temperature	182 - 204 Â°C	360 - 400 Â°F	Extrusion Transition Zone
	177 - 216 Â°C	350 - 420 Â°F	Injection Molding
	188 - 210 Â°C	370 - 410 Â°F	Extrusion Metering Zone
Front Barrel Temperature	177 - 216 Â°C	350 - 420 Â°F	Injection Molding
	188 - 210 Â°C	370 - 410 Â°F	Extrusion
Nozzle Temperature	188 - 221 Â°C	370 - 430 Â°F	Injection Molding
Die Temperature	193 - 216 Â°C	380 - 420 Â°F	Extrusion
Melt Temperature	182 - 221 Â°C	360 - 430 Â°F	Injection Molding
	193 - 216 Â°C	380 - 420 Â°F	Extrusion
Mold Temperature	10.0 - 65.6 Â°C	50.0 - 150 Â°F	Injection Molding
Roll Temperature	21.1 - 48.9 Â°C	70.0 - 120 Â°F	Extrusion
Drying Temperature	82.2 Â°C	180 Â°F	
Dry Time	3 hour	3 hour	
Injection Pressure	0.0689 - 1.03 MPa	10.0 - 150 psi	Injection Molding Back Pressure
Screw Speed	100 - 200 rpm	100 - 200 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China