

Teknor Apex Sinpolene TPP1010 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Availability: Africa & Middle East; Latin America; Asia Pacific; South America Talc Filler, 10% Filler by Weight Uses: Appliance Components;

Housings Forms: Pellets Processing Method: Injection Molding Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinpolene-TPP1010-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.955 g/cc	0.955 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
Melt Flow	12.0 g/10 min @Load 2.16 kg, Temperature 230 Â°C	12.0 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	39.0 MPa	5660 psi	ASTM D638
Elongation at Break	42 %	42 %	ASTM D638
Flexural Strength	50.0 MPa	7250 psi	ASTM D790
Flexural Modulus	2.18 GPa	316 ksi	ASTM D790
Izod Impact, Notched	0.278 J/cm @Temperature 22.8 Â°C	0.520 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	126 Â°C	259 Â°F	Unannealed; ASTM D648
Vicat Softening Point	153 Â°C	307 Â°F	Loading 1 (10N); ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China