

Teknor Apex Sinvicomp DFR 5806 Polyvinyl Chloride, Rigid

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Availability: Asia Pacific Features: Good Impact Resistance Uses: Profiles Forms: Powder Processing Method: Extrusion Information

Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinvicomp-DFR-5806-Polyvinyl-Chloride-Rigid.php

Physical Properties	Metric	English	Comments
Apparent Bulk Density	0.650 g/cc	0.0235 lb/in ³	ASTM D1895

Mechanical Properties	Metric	English	Comments
Flexural Modulus	0.220 GPa	31.9 ksi	ISO 178

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	190 °C	374 °F	Congo Red; ASTM D2115-92
	@Time >=3600 sec	@Time >=1.00 hour	
Vicat Softening Point	78.9 °C	174 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China