

Teknor Apex Sinvicomp SRF 3705 Polyvinyl Chloride, Rigid

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Availability: Asia Pacific Features: Medium Impact Resistance Uses: Fittings Forms: Pellets Processing Method: Injection

Molding Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinvicomp-SRF-3705-Polyvinyl-Chloride-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	49.0 MPa	7110 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	190 °C @Time 1800 sec	374 °F @Time 0.500 hour	Congo Red; BS 2782
Vicat Softening Point	91.1 °C	196 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China