

## **Teknor Apex Telcar® 90-E607D-88NT Ethylene Vinyl Acetate Copolymer**

Category: Polymer, Thermoplastic, Ethylene Vinyl Acetate

## **Material Notes:**

Notes: The Specialty Compounding Division offers a proprietary line of cap-liner compounds designed for carbonated soft drinks. These are proven products that have been used commercially for several years. These compounds are available pre-colored or natural, and can be tailored to specific needs. Forms: PelletsInformation Provided by Teknor Apex

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Teknor-Apex-Telcar-90-E607D-88NT-Ethylene-Vinyl-Acetate-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	ASTM D792
Melt Flow	12.0 g/10 min	12.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	88	88	15 seconds; ASTM D2240
Tensile Strength at Break	7.58 MPa	1100 psi	ASTM D638
Elongation at Break	470 %	470 %	ASTM D638

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China