

Teknor Apex Telcar® 95-T0769V-90NT Ethylene Vinyl Acetate Copolymer

Category: Polymer, Thermoplastic, Ethylene Vinyl Acetate

Material Notes:

Notes: The Specialty Compounding Division offers a proprietary line of cap-liner compounds designed for carbonated soft drinks. These are proven products that have been used commercially for several years. These compounds are available pre-colored or natural, and can be tailored to specific needs. Forms: PelletsInformation Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-95-T0769V-90NT-Ethylene-Vinyl-Acetate-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	ASTM D792
Melt Flow	16.0 g/10 min	16.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	ASTM D2240
Tensile Strength at Break	9.79 MPa	1420 psi	ASTM D638
Elongation at Break	750 %	750 %	ASTM D638
Tensile Modulus	0.00517 GPa	0.750 ksi	ASTM D638

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China