

## Thermoseal KLINGERSIL® C-6400 SBR Binder Gasketing

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

**Material Notes:**

Synthetic FiberModified SBR BinderGood Anti-Stick PropertiesGood Steam SheetInformation provided by Thermoseal Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Thermoseal-KLINGERSIL-C-6400-SBR-Binder-Gasketing.php](http://www.lookpolymers.com/polymer_Thermoseal-KLINGERSIL-C-6400-SBR-Binder-Gasketing.php)

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in <sup>3</sup>	ASTM F1315
Thickness	1588 microns	62.52 mil	Thickness tested

Electrical Properties	Metric	English	Comments
Dielectric Strength	16.0 kV/mm	406 kV/in	ASTM D149-95a

Descriptive Properties	Value	Comments
Color	White or Black	(Top/Bottom)
Compressibility	8 percent	ASTM F36J
Creep Relaxation	20 percent	1/32", ASTM F38B
Gas Permeability	<0.3 ml/min	DIN 3535/6
Klinger Hot Compression Test	11 percent	Additional, Thickness Decrease 572°F (300°C)
	12 percent	Initial, Thickness Decrease 73°F (23°C)
Leachable Chloride Content	200 ppm	FSA Method (Typical)
Recovery	>50 percent	ASTM F36J
Sealability	<0.2 ml/hr	1/32", ASTM F37A
Thickness Increase	0-10%	ASTM F146 after immersion in ASTM Oil 1, 5h/300°F (149°C)
	0-10%	ASTM Fuel B, 5h/73°F (23°C)
	0-5%	ASTM Fuel A, 5h/73°F (23°C)
	10-25%	ASTM Oil IRM903, 5h/300°F (149°C)
Weight Increase	<25%	ASTM F146 after immersion in Fuel B 5h/73°F (23°C)

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**