

## ThyssenKrupp N-A-XTRA® 550 Structural Steel

Category : Metal , Ferrous Metal , Carbon Steel , Low Carbon Steel

### Material Notes:

This Material Specification applies to quenched and tempered heavy plates made of the special structural steel N-A-XTRA® This steel can be supplied in 3 different grades with a minimum yield strength of 550, 620 and 700 MPa. All steel grades can be delivered in two qualities with different toughness properties. 1) Quality for low service temperature with minimum impact energy at - 40 °C (N-A-XTRA® M) in a thickness range from 3 to 100 mm. 2) Special quality for low service temperature with minimum impact energy at - 60 °C (classic N-A-XTRA®) in a thickness range from 3 to 50 mm. Application: The steels are used for welded constructions of all kinds, such as pressure vessels, penstocks, bridges and structures, as well as transport vehicles, mobile cranes, mining equipment, hoistings and earth moving equipment, which are utilized in different types of climatic conditions. If continuous yielding occurs, the yield strength is determined as Rp0,2. Information Provided by Thyssen Krupp

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ThyssenKrupp-N-A-XTRA-550-Structural-Steel.php](http://www.lookpolymers.com/polymer_ThyssenKrupp-N-A-XTRA-550-Structural-Steel.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 410 MPa	>= 59500 psi	
	@Strain 0.200 %, Temperature 400 °C	@Strain 0.200 %, Temperature 752 °F	
	>= 425 MPa	>= 61600 psi	
	@Strain 0.200 %, Temperature 350 °C	@Strain 0.200 %, Temperature 662 °F	
	>= 440 MPa	>= 63800 psi	
	@Strain 0.200 %, Temperature 300 °C	@Strain 0.200 %, Temperature 572 °F	
	>= 455 MPa	>= 66000 psi	
	@Strain 0.200 %, Temperature 250 °C	@Strain 0.200 %, Temperature 482 °F	
	>= 475 MPa	>= 68900 psi	
	@Strain 0.200 %, Temperature 200 °C	@Strain 0.200 %, Temperature 392 °F	
	>= 510 MPa	>= 74000 psi	
	@Strain 0.200 %, Temperature 150 °C	@Strain 0.200 %, Temperature 302 °F	
	>= 530 MPa	>= 76900 psi	
	@Strain 0.200 %, Temperature 100 °C	@Strain 0.200 %, Temperature 212 °F	
Elongation at Break	>= 16 %	>= 16 %	

Mechanical Properties	27.0 J Metric	19.9 ft-lb English	Comments
	@Temperature -60.0 °C	@Temperature -76.0 °F	
	30.0 J	22.1 ft-lb	Transverse
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	30.0 J	22.1 ft-lb	Longitudinal
	@Temperature -60.0 °C	@Temperature -76.0 °F	
	35.0 J	25.8 ft-lb	Transverse
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	40.0 J	29.5 ft-lb	Longitudinal
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	40.0 J	29.5 ft-lb	Transverse
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	50.0 J	36.9 ft-lb	Longitudinal
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	60.0 J	44.3 ft-lb	Longitudinal
	@Temperature 0.000 °C	@Temperature 32.0 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 1.5 %	<= 1.5 %	
Carbon, C	<= 0.20 %	<= 0.20 %	
Chromium, Cr	<= 1.5 %	<= 1.5 %	
Manganese, Mn	<= 1.6 %	<= 1.6 %	
Molybdenum, Mo	<= 0.60 %	<= 0.60 %	
Phosphorous, P	<= 0.020 %	<= 0.020 %	
Silicon, Si	<= 0.80 %	<= 0.80 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China