

ThyssenKrupp XABO® 960 Structural Steel

Category : Metal , Ferrous Metal , Carbon Steel , Low Carbon Steel

Material Notes:

This Material Specification applies to liquid-quenched and tempered heavy plates from 3 up to 100 mm in thickness, made of the high-strength special structural steels XABO® 890 and XABO® 960. Application: The steels are used for welded constructions of all kinds such as transport vehicles, mobile cranes, hoistings and mining equipment, pressure vessels and penstocks. Information Provided by Thyssen Krupp

Order this product through the following link:

http://www.lookpolymers.com/polymer_ThyssenKrupp-XABO-960-Structural-Steel.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	900 - 1050 MPa	131000 - 152000 psi	80<x=100mm
	920 - 1070 MPa	133000 - 155000 psi	60<x=80mm
	970 - 1100 MPa	141000 - 160000 psi	50<x=60mm
	980 - 1150 MPa	142000 - 167000 psi	
	@Thickness 50.0 mm	@Thickness 1.97 in	
Tensile Strength, Yield	>= 850 MPa	>= 123000 psi	80<x=100mm
	>= 870 MPa	>= 126000 psi	60<x=80mm
	>= 920 MPa	>= 133000 psi	50<x=60mm
	>= 960 MPa	>= 139000 psi	
	@Thickness 50.0 mm	@Thickness 1.97 in	
Elongation at Break	>= 10 %	>= 10 %	
Charpy Impact	27.0 J	19.9 ft-lb	Transverse
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	30.0 J	22.1 ft-lb	Transverse
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	30.0 J	22.1 ft-lb	Longitudinal
	@Temperature -40.0 °C	@Temperature -40.0 °F	
35.0 J	25.8 ft-lb	Transverse	
	@Temperature 0.000 °C	@Temperature 32.0 °F	
40.0 J	29.5 ft-lb	Longitudinal	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
50.0 J	36.9 ft-lb		

Mechanical Properties	Metric @ Temperature 0.000 °C	English @ Temperature 32.0 °F	Longitudinal Comments
Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.80 %	<= 0.80 %	
Carbon, C	<= 0.18 %	<= 0.18 %	
Chromium, Cr	<= 0.80 %	<= 0.80 %	
Manganese, Mn	<= 1.6 %	<= 1.6 %	
Molybdenum, Mo	<= 0.70 %	<= 0.70 %	
Nickel, Ni	<= 2.0 %	<= 2.0 %	
Phosphorous, P	<= 0.020 %	<= 0.020 %	
Silicon, Si	<= 0.50 %	<= 0.50 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	
Vanadium, V	<= 0.10 %	<= 0.10 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China