

Tipco Tipcolite® TX 311 Phenolic Compound, Wood Flour & Minerals, having Soft Flow & High Strength

Category : Polymer , Thermoset , Phenolic

Material Notes:

Soft Flow Phenolic Compound, Reinforced with Wood Flour & Minerals
Applications: Switchgear, HRC Fuses
Processing: Injection Moulding
Information provided by the Manufacturer, Tipco Industries Ltd., India.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tipco-Tipcolite-TX-311-Phenolic-Compound-Wood-Flour-Minerals-having-Soft-Flow-High-Strength.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ASTM D792
Apparent Bulk Density	0.630 g/cc	0.0228 lb/in ³	TRM-37
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	49.0 MPa	7110 psi	ASTM D638
Flexural Yield Strength	80.0 MPa	11600 psi	ASTM D790
Izod Impact, Unnotched (ISO)	2.20 kJ/m ²	1.05 ft-lb/in ²	ASTM D256

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.59e+10 ohm-cm	1.59e+10 ohm-cm	ASTM D257
Surface Resistance	1.59e+9 ohm	1.59e+9 ohm	ASTM D257
Dielectric Strength	8.50 kV/mm	216 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China