

## Tipco Tipcolite® TX 312 Phenolic Compound, Wood Flour & Minerals having Soft Flow & Lower Density

Category : Polymer , Thermoset , Phenolic

**Material Notes:** 

Soft Flow Phenolic Compound, Reinforced with Wood Flour & MineralsApplications: Switchgear, HRC FusesProcessing: Injection

MouldingInformation provided by the Manufacturer, Tipco Industries Ltd., India.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Tipco-Tipcolite-TX-312-Phenolic-Compound-Wood-Flour-Minerals-having-Soft-Flow-Lower-Density.php

| Physical Properties   | Metric       | English                   | Comments  |
|-----------------------|--------------|---------------------------|-----------|
| Density               | 1.37 g/cc    | 0.0495 lb/in³             | ASTM D792 |
| Apparent Bulk Density | 0.630 g/cc   | 0.0228 lb/in <sup>3</sup> | TRM-37    |
| Linear Mold Shrinkage | 0.0060 cm/cm | 0.0060 in/in              | ASTM D955 |

| Mechanical Properties        | Metric                 | English        | Comments  |
|------------------------------|------------------------|----------------|-----------|
| Tensile Strength, Ultimate   | 44.0 MPa               | 6380 psi       | ASTM D638 |
| Flexural Yield Strength      | 75.0 MPa               | 10900 psi      | ASTM D790 |
| Izod Impact, Unnotched (ISO) | 2.20 kJ/m <sup>2</sup> | 1.05 ft-lb/in² | ASTM D256 |

| Electrical Properties | Metric          | English         | Comments  |
|-----------------------|-----------------|-----------------|-----------|
| Volume Resistivity    | 3.16e+10 ohm-cm | 3.16e+10 ohm-cm | ASTM D257 |
| Surface Resistance    | 3.16e+9 ohm     | 3.16e+9 ohm     | ASTM D257 |
| Dielectric Strength   | 8.00 kV/mm      | 203 kV/in       | ASTM D149 |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China