

Tisan TISLAMID® 66 Impact Modified Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

TISLAMID has a wide area of application in electric/electronic, automotive, durable goods and telecommunications industries. It demonstrates characteristics such as Excellent chemical resistance Electric isolation Easy processability High mechanical resistance Excellent flame retardance High moisture absorption Excellent temperature resistance High performance / affordable price Abrasion resistance TISLAMID has an excellent resistance to weak alkalis and organic solvents. It has a good resistance to weak acids, alcohols, hydrocarbons, and engine fuels. It has a medium resistance to strong alkalis and a weak resistance to strong acids.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tisan-TISLAMID-66-Impact-Modified-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.016 cm/cm	0.016 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	49.0 MPa	7110 psi	ISO 527-2
Tensile Strength, Yield	50.0 MPa	7250 psi	ISO 527-2
Elongation at Break	2.0 %	2.0 %	ISO 527-2
Elongation at Yield	2.0 %	2.0 %	ISO 527-2
Modulus of Elasticity	1.80 GPa	261 ksi	ISO 527-2
Izod Impact, Notched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	255 - 260 °C	491 - 500 °F	
Flammability, UL94	HB	HB	
Glow Wire Test	650 °C	1200 °F	60695-2-10

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	TS EN 60112

Processing Properties	Metric	English	Comments
Feed Temperature	70.0 - 90.0 °C	158 - 194 °F	

Rear Barrel Temperature Processing Properties	260 - 280 °C Metric	500 - 536 °F English	Aft-1. Region Temperature Comments
Middle Barrel Temperature	260 - 280 °C	500 - 536 °F	Mid-2. Region Temperature
Front Barrel Temperature	260 - 280 °C	500 - 536 °F	Pre-3. Region Temperature
Nozzle Temperature	250 - 270 °C	482 - 518 °F	
Melt Temperature	260 - 290 °C	500 - 554 °F	
Drying Temperature	90.0 - 100 °C	194 - 212 °F	Predrying Temperature
Dry Time	3 - 4 hour	3 - 4 hour	Predrying Time
Moisture Content	2.0 %	2.0 %	ISO 62

Descriptive Properties	Value	Comments
Block Temperature	75-85°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China