

Total CD 4300 HDPE extrusion

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Extruded

Material Notes:

Applications: General profile extrusion, irradiation-crosslinked products
Information provided provided by Total Petrochemicals. Total Petrochemicals acquired former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-CD-4300-HDPE-extrusion.php

Physical Properties	Metric	English	Comments
Density	0.947 g/cc	0.0342 lb/in ³	ASTM D 792
Environmental Stress Crack Resistance	>= 1000 hour	>= 1000 hour	ASTM D1693 cond. C 100% Igepal
Melt Flow	0.28 g/10 min @Load 2.16 kg	0.28 g/10 min @Load 4.76 lb	ASTM D 1238
High Load Melt Index	20 g/10 min @Load 21.6 kg	20 g/10 min @Load 47.6 lb	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63	63	ASTM D 2240
Tensile Strength, Yield	>= 22.8 MPa	>= 3300 psi	ASTM D 638 type IV
Elongation at Break	>= 600 %	>= 600 %	ASTM D 638 type IV
Flexural Modulus	0.793 GPa	115 ksi	ASTM D 790

Thermal Properties	Metric	English	Comments
Melting Point	126 °C	259 °F	ASTM D3417

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China