

Total Finaclear® 520 Clear Impact Polystyrene (discontinued **)

Category: Polymer, Thermoplastic, Polystyrene (PS)

Material Notes:

Finaclear® 520 is a clear high styrenic styrene-butadiene (SBS) elastomer, providing dramatically improved impact properties and tear resistance to finished articles. Complemented by inherent reprocessing and recycling capability, Finaclear® 520 is a well established material in both food and non-food transparent packaging applications. Finaclear® 520 complies with most of the food regulations of European countries and with the Food and Drug Administration (FDA) in the USA.ApplicationFinaclear® 520 is designed for mono- and multilayer sheet extrusion/thermoforming, cast and blown film extrusion. Due to its specific structure and the well balanced styrene/butadiene ratio, Finaclear® 520 is the material of choice to reach an optimal balance between high impact, good clarity, brilliancy and cost. Information provided provided by Total Petrochemicals. Total Petrochemicals includes former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-Finaclear-520-Clear-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments	
Bulk Density	0.620 g/cc	0.0224 lb/in³	ASTM D1895B	
Density	1.01 g/cc	0.0365 lb/in³	Finaprene 2602	
	7.5 g/10 min	7.5 g/10 min		
Melt Index of Compound	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	ASTM D1238G	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	<= 200 %	<= 200 %	ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	ASTM D790
Izod Impact, Notched	0.260 J/cm	0.487 ft-lb/in	ASTM D256A
	0.250 J/cm	0.468 ft-lb/in	ASTM D256A
	@Temperature -30.0 °C	@Temperature -22.0 °F	AO I III DECOA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	65.0 °C	149 °F	120°C/h; ASTM D648
Vicat Softening Point	80.0°C	176 °F	ASTM D1525

Optical Properties	Metric	English	Comments	



Optical Properties	Metric	2.5 % English	ASTM 01003 Comments
Transmission, Visible	91 %	91 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China